



FINISHES



Honed



Brushed



Pumiced



Tumbled

The neutral beige tones and durable nature of Jasper Travertine, previously known as Classic Travertine, make it an unpretentious stone choice with timeless appeal. This material can be filled and honed for a more refined look, or left natural for a more relaxed aesthetic.

APPLICATIONS	SPECIFICATIONS	TECHNICAL DATA																									
<ul style="list-style-type: none"> <li>• Commercial Paving</li> <li>• Residential Paving</li> <li>• Thin Veneer</li> <li>• L Shaped Corners</li> </ul>	<ul style="list-style-type: none"> <li>• Architectural Items</li> </ul>	<table border="0"> <tr> <td>Source:</td> <td>Non-domestic</td> <td>ASTM C97</td> <td>Density (gr/m3)</td> <td>2.70</td> </tr> <tr> <td>Color Range:</td> <td>Cream</td> <td>ASTM C170</td> <td>Compressive Strength (kg/cm2)</td> <td>650</td> </tr> <tr> <td>Std. Block Size:</td> <td>TBC</td> <td>ASTM C880</td> <td>Flex. Strength (kg/cm2)</td> <td>83</td> </tr> <tr> <td>Std. Thickness:</td> <td>TBC</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Std. Lead Time:</td> <td>10 – 14 weeks</td> <td></td> <td></td> <td></td> </tr> </table>	Source:	Non-domestic	ASTM C97	Density (gr/m3)	2.70	Color Range:	Cream	ASTM C170	Compressive Strength (kg/cm2)	650	Std. Block Size:	TBC	ASTM C880	Flex. Strength (kg/cm2)	83	Std. Thickness:	TBC				Std. Lead Time:	10 – 14 weeks			
Source:	Non-domestic	ASTM C97	Density (gr/m3)	2.70																							
Color Range:	Cream	ASTM C170	Compressive Strength (kg/cm2)	650																							
Std. Block Size:	TBC	ASTM C880	Flex. Strength (kg/cm2)	83																							
Std. Thickness:	TBC																										
Std. Lead Time:	10 – 14 weeks																										

[www.maiden-stone.com/products/jasper\\_travertine](http://www.maiden-stone.com/products/jasper_travertine)

Stone is a natural product that varies in color, texture, and fossil activity (if applicable). All technical data is deemed to be correct but is not guaranteed and should be independently verified.