




FINISHES



Honed



Brushed

A classic French limestone in the truest sense, Mistral Limestone sorts to light and dark ranges at the quarry level which can then be used singularly or blended together in the finished product. The soft shades of creamy white to beige of the light range, and taupe to café au lait of the dark range are mottled throughout the limestone in a gently ribboned pattern. This elegant and refined material is accompanied by broad fabrication possibilities that make it an obvious choice for interior and exterior applications that will have timeless appeal. *

APPLICATIONS	SPECIFICATIONS	TECHNICAL DATA															
<ul style="list-style-type: none"> Commercial Paving Residential Paving Thin Veneer L Shaped Corners Architectural Items Freeze Thaw Veneer 	<p>Source: Non-domestic</p> <p>Color Range: Beige, Cream</p> <p>Std. Block Size: TBC</p> <p>Std. Thickness: TBC</p> <p>Std. Lead Time: 10 – 14 weeks</p>	<table border="0"> <tr> <td>ASTM C97</td> <td>Density (kg/m3)</td> <td>2,130</td> </tr> <tr> <td>ASTM C97</td> <td>Absorption (%)</td> <td>15-20</td> </tr> <tr> <td>ASTM C99</td> <td>Modulus of Rupture (psi/avg)</td> <td>1,561</td> </tr> <tr> <td>ASTM C170</td> <td>Compres. Strength (MPa)</td> <td>40-60</td> </tr> <tr> <td>ASTM C880</td> <td>Flexural Strength (MPa)</td> <td>4-8</td> </tr> </table>	ASTM C97	Density (kg/m3)	2,130	ASTM C97	Absorption (%)	15-20	ASTM C99	Modulus of Rupture (psi/avg)	1,561	ASTM C170	Compres. Strength (MPa)	40-60	ASTM C880	Flexural Strength (MPa)	4-8
ASTM C97	Density (kg/m3)	2,130															
ASTM C97	Absorption (%)	15-20															
ASTM C99	Modulus of Rupture (psi/avg)	1,561															
ASTM C170	Compres. Strength (MPa)	40-60															
ASTM C880	Flexural Strength (MPa)	4-8															

www.maiden-stone.com/products/mistral_limestone

* Please note: Mistral Limestone is subject to quarry block procurement. Please call us for a current status on the availability of this material.

Stone is a natural product that varies in color, texture, and fossil activity (if applicable). All technical data is deemed to be correct but is not guaranteed and should be independently verified.